

Product Features

- Sulfuric acid immobilized as a gel using the gaseous SiO₂ which imported from Germany as main electrolyte, The GEL state electrolyte prevents leakage and layering;
- Low resistance PVC-SiO₂ micro-porous separator ensure low internal resistance;
- Paste type, thick plate design, good corrosion resistance, long service life;
- Advanced gel technology, the battery has good charge acceptance ability and good performance in poor power supply condition.

Application



- Telecom
- Nuclear power, standby power supply
- Renewable Energy;
- CATV
- General electronic
- EPS/UPS

Compliant Standards

- IEC 60896-21/22: 2004
- IEC 61427-2005
- DIN43539-T5 1984
- YD/T1360-2005
- GB/T 22473-2008
- Passed ISO9001、ISO14001、OHSAS18001、UL and CE certificate
- Eurobat guide;

Safety

- installation compliant with:EN50272-2







Battery Model	6GFMJ-65			
Designed Life	12 Years			
Capacity(25°C)	10HR(6.5A,1.80V)	5HR(11.1A,1.80V)	3HR(16.3A,1.80V)	1HR(35.8A,1.80V)
	65AH	55.5AH	48.9AH	35.8AH
Dimensions	Length	Width	Height	Total Height
	310mm	174mm	209mm	236mm
Approx. Weight	30kg			
Internal Resistance	7.35mΩ			
Max Discharge Current	833A(3 Sec.)			
Self Discharge	≤2% per months (25°C)			
Charge Voltage(25°C)	Cycle use		Float use	
	13.98V(-21mV/°C), max charge current:13A		13.38V(-21mV/°C)	

Discharge parameter:

Constant current discharge data (25°C, A)																		
End voltage (V/cell)	5min	10 min	15 min	20 min	30 min	45 min	1h	1.5h	2h	3h	5h	10h	20h	24h	48h	100h	120h	240h
1.60	181.5	132.3	103.1	86.5	63.2	49.5	37.6	29.2	22.4	17.0	11.4	6.5	3.51	3.00	1.58	0.81	0.71	0.38
1.65	172.3	127.7	101.1	85.1	62.5	48.6	36.9	28.8	22.4	17.0	11.4	6.5	3.51	3.00	1.58	0.81	0.71	0.38
1.70	162.2	121.0	99.1	83.1	61.8	47.1	36.9	28.3	22.4	17.0	11.4	6.5	3.51	3.00	1.58	0.81	0.71	0.38
1.75	150.3	112.4	95.7	79.8	59.9	45.8	36.2	28.0	22.4	17.0	11.4	6.5	3.51	3.00	1.58	0.81	0.71	0.38
1.80	128.3	102.4	89.8	74.5	56.6	44.1	35.8	27.2	21.7	16.3	11.1	6.5	3.38	2.86	1.58	0.81	0.71	0.38

Constant power discharge data (25°C, W/cell)																		
End voltage (V/cell)	5min	10 min	15 min	20 min	30 min	45 min	1h	1.5h	2h	3h	5h	10h	20h	24h	48h	100h	120h	240h
1.60	320.5	240.0	188.4	158.1	118.5	89.1	69.4	54.0	42.3	30.6	20.9	12.4	6.6	5.95	3.16	1.63	1.43	0.76
1.65	298.1	231.2	184.3	156.3	117.5	88.3	68.2	53.6	42.3	30.6	20.9	12.2	6.6	5.95	3.16	1.63	1.43	0.76
1.70	272.5	218.5	178.1	153.1	115.8	87.1	68.2	53.0	42.3	30.6	20.9	12.2	6.6	5.95	3.16	1.63	1.43	0.76
1.75	251.2	202.5	172.6	147.3	112.8	85.1	67.0	52.5	42.3	30.6	20.9	12.1	6.6	5.95	3.16	1.63	1.43	0.76
1.80	233.7	184.6	164.8	138.0	107.5	82.0	66.0	51.3	41.2	29.8	19.8	11.8	6.4	5.72	3.16	1.63	1.43	0.76

Performance Curve:


ISO9001 ISO14001 OHSAS18001

Address: NO.1 Shengyang Road, Qufu, Shandong 273100 China

Tel: +86-537-4438666-6028

Fax: +86-537-4411936

E-mail: sales@sacredsunsun.cn

http://www.sacredsunsun.com